



Tubular Gel OPzV Cell


Discover® Tubular Gel OPzV batteries are maintenance-free and provide superior deep cycling performance and reliability for demanding commercial, industrial and residential applications. Providing reliable energy storage for Stationary Backup and Telecom Networks, and Renewable Energy applications with its Advanced Tubular Plate Technology to deliver long service life. Discover® Tubular Gel OPzV batteries provide maximum efficiency per discharge-charge cycle, and proven reliability in remote, high temperature, or unstable power network installations.

MECHANICAL DRAWINGS





Terminal (M10)



MECHANICAL SPECIFICATIONS

Voltage	2			
Industry Reference	Tubular Gel OPzV			
Length (A)	8.2 in	210 mm		
Width (B)	7.5 in	191 mm		
Height (C)	25.3 in	644 mm		
Total Height (D)	26.4 in	672 mm		
Weight	146 lbs	66 kgs		
Terminal	M10			
Poles	4			
Cell(s)	1			
Container	ABS			

ELECTRICAL SPECIFICATIONS

	20% DOD	2.05V				
Reference LVD / I10	50% DOD	1.97V				
	80% DOD	1.91V				
Cycle Life	20% DOD	7000 cycles				
	50% D0D 2950 cycles					
	80% DOD	1900 cycles				
Internal Resistance		0.39 mΩ				
Short Circuit		4550 A				
Self Discharge		2-3% per month				
Maximum Operating Temperature		-35°C / -31°F 50°C / 122°F				
Electrolyte		Gel				

+ 1.778.776.3288

ELECTRICAL SPECIFICATIONS

240 HR	120 HR	100 HR	20 HR	10 HR	5 HR	3 HR	1 HR
1.85 Volts Per Cell (VPC)		1.75 Volts Per Cell (VPC)					
1313 AH	1306 AH	1287 AH	1012 AH	920 AH	831 AH	720 AH	445 AH

BENEFITS & FEATURES

Long Service Life

Tubular positive plates with non-woven polyester gauntlets are designed to prevent active material plate shedding and provide the highest cycling expectancy amongst lead acid technologies, particularly in PSoC (Partial State of Charge) operation.

High energy density tubular plates in combination with lead calcium alloy reduces self discharge and charge current requirements during float operation and extends battery service life.

Performance and Reliability

Special sliding pole terminals are designed to accommodate natural grid growth occurrence throughout battery lifetime. Battery containers are made of Acrylonitrile Butadiene Styrene(ABS) and Styrene Acrylonitrile (SAN) to endure high impact and heat environments.

Maintenance and Optimization

OPzV Gel batteries are valve-regulated, non-spillable and completely maintenancefree and available with the option to be horizontally mounted.

Safety

All products are tested and certified to multiple international safety standards for use in Photovoltaic and Stationary applications. Flame retardant containers are available upon request.

Lowest Total Cost of Ownership

OPzVTubular batteries provide the Lowest Total Cost of Ownership (TCO) amongst lead acid technologies. Further savings can be achieved in Hybrid systems through diesel abatement and peak shaving.

CERTIFIED QUALITY

Discover and its manufacturing facilities are fully certified to ISO 9001/14001 and OSHA 18001 standards. OPzS and OPzVTubular products are also tested in compliance to multiple international standards:


- Eurobat "Long Life" classification
- IEC 60896-21/22 (OPzV) and IEC60896-11 (OPzS) test standard for stationary applications
- IEC 61427 test standard for photovoltaic energy systems
- EN50272-1 and EN50272-2 safety requirements
- DIN 40742 (OPzV) and DIN 40736 (OPzS) standard for stationary tubular plate cells
- UN 2800 (US DOT Compliance)









EXPECTED NUMBER OF CYCLES IN RELATION TO THE DEPTH OF DISCHARGE




CAPACITY IN RELATION TO THE TEMPERATURE




SELF-DISCHARGE CHARACTERISTICS



EXPECTED SERVICE LIFE IN RELATION TO OPERATING TEMPERATURE



Float Voltage Setting in Relation to Operating Temperature



Discover® attempts to ensure the correctness of the product description and data contained herein. We reserve the right to change designs, specifications and pricing at one tites without notice or a policytion. It is the respecificity of the conduct of this information to use it is not the respective product of the conduct of this information to use it is not to respect the product of the conduct of this information to use it is not a conduction.